

Ravamid® A GF 15 BK

Polyamide 66
Industrial Quality Compound

Description:

Polyamide 66 black containing recycled material, 15% glass fiber reinforced, also available Heat Stabilized (H) and UV Stabilized (UV)

General

Density	ISO 1183	1.22	g/cm ³
Mold shrinkage (Parallel)		0.50	%
Mold shrinkage (Perpendicular)		0.90	%

Thermal

HDT/A (1,82MPa)	ISO 75A	190	°C
-----------------	---------	-----	----

Mechanical

Izod notched impact strength (23°C)	ISO 180	5	kJ/m ²
Tensile stress at yield	ISO 527	75	MPa
Tensile stress at break	ISO 527	70	MPa
Elongation at break	ISO 527	5	%
Tensile modulus	ISO 527	4000	MPa
Flex modulus	ISO 178	3700	MPa

Flammability

Burning rate (2,0 mm)	ISO 3795	<100	mm/min
Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C

Various

Humidity	ISO 960	≤ 0.20	%
----------	---------	--------	---

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters

Moerenstraat 85A
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11
Fax: +32 (0)14 67 20 12

www.ravago.com
manufacturing@ravago.com

Issue Date:
Apr 2020