

# Ravamid® A T BK

Polyamide 66  
Industrial Quality Compound

## Description:

Polyamide 66 black containing recycled material, impact modified, also available Heat Stabilized (H) and UV Stabilized (UV)

## General

Density	ISO 1183	1.11	g/cm <sup>3</sup>
Linear mould shrinkage	ISO 2577	1.5	%

## Thermal

HDT/A (1,82MPa)	ISO 75A	65	°C
-----------------	---------	----	----

## Mechanical

Izod notched impact strength (23 °C)	ISO 180	10	kJ/m <sup>2</sup>
Tensile strength at yield (23 °C)	ISO 527	55	MPa
Tensile strength at break (23 °C)	ISO 527	53	MPa
Elongation at break (23 °C)	ISO 527	23	%
Flexural modulus (23 °C)	ISO 178	2400	MPa

## Flammability

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C

## Various

Humidity	ISO 960	≤0.25	%
----------	---------	-------	---

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## Ravago Group Headquarters

Moerenstraat 85A  
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11  
Fax: +32 (0)14 67 20 12

www.ravago.com  
manufacturing@ravago.com

Issue Date:  
Feb 2018