



Polyamide 6 Industrial Quality Compound

Description:

Poliamyde 6 black containing recycled material, 30% glass fiber reinforced, high impact modified, also available Heat Stabilized (H) and UV Stabilized (UV)

General

Density	ISO 1183	1.31	g/cm³	
Mold shrinkage (Parallel)		0.15	%	
Mold shrinkage (Perpendicular)		0.70	%	

Thermal

HDT/A (1,82MPa)	ISO 75A	175	°C	

Mechanical

Izod notched impact strength (23 °C)	ISO 180	12	kJ/m²	
Charpy notched impact strength (23 °C)	ISO 179	12	kJ/m²	
Charpy unnotched impact strength (23 °C)	ISO 179	65	kJ/m²	
Tensile strength at break (23 °C)	ISO 527	124	MPa	
Elongation at break (23 °C)	ISO 527	5.0	%	
Tensile modulus (23 °C)	ISO 527	7800	MPa	
Flexural modulus (23 °C)	ISO 178	7000	MPa	
` '				

Flammability

Flammability (3,2mm)	UL94	НВ		
Flammability (1,6mm)	UL94	НВ		
Burning rate (FMVSS 302)	ISO 3795	<100	mm/min	
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C	

Various

	Humidity	ISO 960	<0.15	%
- 1				

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters

Moerenstraat 85A Tel: +32 (0)14 67 25 11 B - 2370 Arendonk Fax: +32 (0)14 67 20 12