

Mafill® CR C 6044 H

Polypropylene
Industrial Quality Compound

Description:

Polypropylene copolymer, industrial quality, heat stabilized in black

General

MFI (230°/2,16kg)	ISO 1133	15	g/10min
-------------------	----------	----	---------

Thermal

HDT/A (1,82MPa)	ISO 75A	50	°C
Vicat softening point (B50 (50N))	ISO 306	58	°C

Mechanical

Izod notched impact strength (23 °C)	ISO 180	10	kJ/m ²
Flexural modulus (23 °C)	ISO 178	1000	MPa

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters