

Mafill® CR CT 1544

Polypropylene
Industrial Quality Compound

Description:

PP Copolymer, 30% talcum filled, low MFI

General

MFI (230°/2,16kg)	ISO 1133	2.5	g/10min
Density	ISO 1183	1,14	g/cm ³

Thermal

HDT/B (0,46MPa)	ISO 75B	80	°C
-----------------	---------	----	----

Mechanical

Charpy notched impact strength (23 °C)	ISO 179	7	kJ/m ²
Tensile modulus (23 °C)	ISO 527	1900	MPa
Flexural modulus (23 °C)	ISO 178	1700	MPa

Various

Ash content (700 °C)	ISO 3451	30	%
----------------------	----------	----	---

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters