

Mafill® CR HC 6644

Polypropylene
Industrial Quality Compound

Description:

PP homopolymer compound, 40% calcium carbonate filled with medium flow capacity, black colour

General

MFI (230°/2,16kg)	ISO 1133	20	g/10min
-------------------	----------	----	---------

Thermal

Vicat softening point (B50 (50N))	ISO 306	90	°C
-----------------------------------	---------	----	----

Mechanical

Izod notched impact strength (23 °C)	ISO 180	2,5	kJ/m ²
Flexural modulus (23 °C)	ISO 178	2300	MPa

Various

Ash content		40	%
-------------	--	----	---

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters