

RAVAGO® PPS ZX-180-GR7-J1-000

RAVAGO®



Product Description : 40% Glass Fiber Reinforced, Polyphenylene Sulfide

Key Features : RAVAGO PPS ZX-180-GR7-J1-000 is FDA compatible, inherently flame retardant PPS GF40 compound

Process Method : Injection Moulding

Uses : Recommended for general applications and purposes

Revision Date : 01.04.2021

	Value	Unit	Standard
Physical			
Density	1,65	gr / cm3	ISO 1183 1-A
Mechanical			
Tensile Stress at Break	155	MPa	ISO 527-1
Elongation at Break	1,5	%	ISO 527-1
Tensile Modulus	14000	MPa	ISO 527-1
Charpy Impact Strength (Notched)	6	kJ/m2	ISO 179/1A
Thermal			
HDT (1.8 Mpa)	255	°C	ISO 75A
Flammability			
Flammability (1,6 mm)	V0	*	UL 94
Flammability (3,2 mm)	V0	*	UL 94

Drying Condition

Drying Time(hr) 3-4

Drying Temperature(C) 140

Molding Condition

Barrel Rear 285-295

Barrel Center 290-300

Barrel Front 295-310



Ravago Petrokimya Uretim A.S.

Main Office : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Plant : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Mail / Web : info@ravagopetrokimya.com.tr

Tel : +90 850 314 70 99

Fax : +90 262 672 10 51

www.ravagopetrokimya.com.tr

RAVAGO® PPS ZX-180-GR7-J1-000

RAVAGO®



Nozzle	290-300
Mould Temperature	140-180

Important Notice;

The above results are obtained from the tests conducted in Ravago Petrokimya laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. Ravago Petrokimya accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.



Ravago Petrokimya Uretim A.S.

Main Office : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Plant : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Mail / Web : info@ravagopetrokimya.com.tr

Tel : +90 850 314 70 99

Fax : +90 262 672 10 51

www.ravagopetrokimya.com.tr