

RavaBio® 1220 ST

Bio based compound

Description:

RavaBio 1220 ST is a low flow polyester compound based, developed for blow film applications and packaging industry.

RavaBio 1220 ST is considered a compostable compound

General

MFI (190°/2,16kg)	ISO 1133	2	g/10min
-------------------	----------	---	---------

Mechanical

Tensile modulus (Film 40 µm)	ISO 527	250	MPa
Tensile strength TD (Film 40 µm)	ISO 527	25	MPa
Tensile strength MD (Film 40 µm)	ISO 527	19	MPa
Elongation at break (Film 40 µm)	ISO 527	480	MPa
Tensile strength at break (23 °C)	ISO 527	40	MPa
Elongation at break (23 °C)	ISO 527	400	%
Tensile modulus (23 °C)	ISO 527	350	MPa

Remark:

Drying

It is a bio polyester compound, highly hygroscopic, before processing needs to be pre-dried, preferable on a dehumidification process, 4 -6 hours at 45-60°C.

Processing conditions for blown film extrusion

Feeding Zone 40-60 °C
 Zone 1 155 °C
 Zone 2 160 °C
 Zone 3 165 °C
 Zone 4 170 °C
 Adapter 165 °C
 Die 165 °C
 Mass temperature Max. 190 °C

PROVISIONAL DATASHEET

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago Recycled Quality are ISO 14021:2016 compliant. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application

Ravago Group Headquarters

Moerenstraat 85A
 B - 2370 Arendonk

Tel: +32 (0)14 67 25 11
 Fax: +32 (0)14 67 20 12

www.ravago.com
 manufacturing@ravago.com

Issue Date:
 May 2022

Page 1 of 1