



RAVALENE® CR L 5245L

Recycled Low Density Polyethylene Resin

OVERVIEW

Description	Recycled light LDPE compound
Applications	Extrusion of blown film, non-pressure pipes & sheets
Additives	None intentionally added
Recycled content	100%
Source	Post-industrial
Visual	Mixed light colors

PHYSICAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
MFI (190°C / 2.16 kg)	1	g/10 min	ISO 1133
Density (base resin)	0.930	g/cm ³	ISO 1183
Ash content (600 °C)	1	%	ISO 3451

EXTRUSION GUIDELINES

Recommended settings	Comparable processing to standard LDPE resins. Contact your local sales representative for specific advice.
-----------------------------	--

Note: Properties not to be construed as specifications

The information contained herein is to our knowledge accurate and reliable as of the date of publication. Ravago extends no warranties regarding fitness for a particular purpose or compliance to specifications and regulations. It is the customer's responsibility to test the product regarding suitability for a specific purpose.