



RAVALENE® CR C 7654

Recycled Linear Low Density Polyethylene Powder

OVERVIEW

Description	Recycled black LLDPE powder for rotational molding
Applications	Rotational molding
Additives	Antioxidant
Recycled content	> 95%
Source	Post-industrial, various sources
Visual	Black

PHYSICAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
MFI (190°C / 2.16 kg)	4	g/10 min	ISO 1133
Density (base resin)	0.935	g/cm ³	ISO 1183
Ash content	1	%	ISO 3451 600°C
Sieve	600	µm	-

EXTRUSION GUIDELINES

Recommended settings	Comparable processing to standard LLDPE rotomolding resins. Contact your local sales representative for specific advice.
-----------------------------	---

Note: Properties not to be construed as specifications

The information contained herein is to our knowledge accurate and reliable as of the date of publication. Ravago extends no warranties regarding fitness for a particular purpose or compliance to specifications and regulations. It is the customer's responsibility to test the product regarding suitability for a specific purpose.