

Ravalene® PE

Recycled compounds

Ravalene® recycled polyethylene compounds are available as LDPE, LLDPE, MDPE and HDPE grades to suit different application requirements. Whether you produce films, pipes, bottles or even rotomolded parts, you can find the right Ravalene® grade to meet your needs.

Why choose Ravalene compounds?

- Contain over 95% certified recycled content from post-industrial sources
- Consistent homogeneous quality
- Available in black and natural colors

Grade Name	Color	MFI (ISO 1133)	Density (ISO 1183)	Typical Applications			
				Film	Pipe	Blow Molding	Rotational Molding
LDPE		190°C/2.16kg					
CR L 5245 L	Light	1.0 g/10min	0.925 g/cm ³	•	•		
CR LS 5241	Natural	1.3 g/10min	0.925 g/cm ³	•			
CR L 6241	Natural	2.0 g/10min	0.925 g/cm ³	•			
CR L 4244	Black	0.5 g/10min	0.93 g/cm ³	•	•		
CR L 5244	Black	1.0 g/10min	0.93 g/cm ³	•	•		
LLDPE		190°C/2.16kg					
CR C 7654	Black	4.0 g/10min	0.935 g/cm ³				•
CR C 6241	Natural	1.7 g/10min	0.92 g/cm ³	•	•		
MDPE		190°C/2.16kg					
CR M 3544	Black	0.5 g/10min	0.938 g/cm ³	•	•		
HDPE		190°C/5kg					
CR H 2041	Natural	1.0 g/10min	0.95 g/cm ³	•	•	•	
CR H 2042	Natural oxidized	1.2 g/10min	0.95 g/cm ³	•	•	•	
CR H 2444	Black	0.7 g/10min	0.95 g/cm ³	•	•	•	
CR H 2544	Black	1.0 g/10min	0.95 g/cm ³	•	•	•	
CR H 3544	Black	1.65 g/10min	0.95 g/cm ³		•		



Let's connect

We would love to discuss further how we can support you with your recycled PE requirements.

www.ravagomanufacturing.com | info@ravagomanufacturing.com | [in Ravago Manufacturing Europe](https://www.linkedin.com/company/ravago-manufacturing-europe)