

Scolefin 62 T 20-1 FR

Polypropylene Prime Compound



Product Description :	20% Mineral Reinforced, Halogenated Flame Retardant, White Colour, Polypropylene Copolymer Compound
Key Features :	SCOLEFIN 62T 20-1 FR is a halogenated, UL 94 FR V0 PPC compound with good strength and stiffness properties
Process Method :	Injection moulding
Uses :	Recommended for general applications and purposes.
Revision Date :	01.12.2020

	Value	Unit	Standard
Physical			
Density	1,32	gr / cm3	ISO 1183 1-A
MFI-Melt Flow Index (230°C, 2.16 kg)	20	gr / 10 min.	ISO 1133-1
Mechanical			
Yield Strength	22	MPa	ISO 527-1
Elongation at Break	30	%	ISO 527-1
Tensile Modulus	1800	MPa	ISO 527-1
Izod Impact Strength (Notched) (23°C)	10	kJ/m2	ISO 180/1A
Flexural Modulus	2000	Mpa	ISO 178
Flammability			
Flammability (1,6 mm)	V0	*	UL 94
Flammability (3,2 mm)	V0	*	UL 94
Thermal			
Ash Content (600 °C)	20	%	ISO 3451-1

Drying Condition

Drying Time(hr)	0-2
Drying Temperature(°C)	80

Molding Condition (°C)



Ravago Petrokimya Uretim A.S.

Main Office : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Plant : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Mail / Web : info@ravagopetrokimya.com.tr

Tel : +90 850 314 70 99

Fax : +90 262 672 10 51

www.ravagopetrokimya.com.tr

Scolefin 62 T 20-1 FR

Polypropylene Prime Compound



1st Zone (hopper)(°C)	180-200
2nd Zone(°C)	200-210
3rd Zone(°C)	210-230
Nozzle(°C)	215
Mold Temperature(°C)	20-40

Important Notice;

The above results are obtained from the tests conducted in Ravago Petrokimya laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. Ravago Petrokimya accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.



Ravago Petrokimya Uretim A.S.

Main Office : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Plant : Coraklar Mah. 5000 Sokak No:7-17 A.O.S.B. Aliaga-Izmir-Turkey

Mail / Web : info@ravagopetrokimya.com.tr

Tel : +90 850 314 70 99

Fax : +90 262 672 10 51

www.ravagopetrokimya.com.tr