

■ Scolefin[®] 38 C 19-0

Polypropylene
Prime Compound

Description:

Polypropylene homopolymer 80% calcium carbonate filled, for thermoforming

General

MFI (230°/2,16kg)	ISO 1133	5	g/10min
Density	ISO 1183	1,95	g/cm ³

Various

Ash content (600 °C)	ISO 3451	80	%
----------------------	----------	----	---

Remark:

Mean particle size (D50) of CaCO₃: 3 micron

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters

Moerenstraat 85A
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11
Fax: +32 (0)14 67 20 12

www.ravago.com
manufacturing@ravago.com

Issue Date:
Feb 2018