

Scolefin[®] 47 B 10

Polypropylene
Prime Compound

Description:

Polypropylene homopolymer 70% barium sulphate filled

General

MFI (230°/2,16kg)	ISO 1133	10	g/10min
Density	ISO 1183	2,05	g/cm ³

Thermal

Vicat softening point (B50 (50N))	ISO 306	90	°C
-----------------------------------	---------	----	----

Mechanical

Izod notched impact strength (23°C)	ASTM D256	3	J/m
Flex modulus	ISO 178	3900	MPa

Flammability

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters

Moerenstraat 85A
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11
Fax: +32 (0)14 67 20 12

www.ravago.com
manufacturing@ravago.com

Issue Date:
Oct 2017