

Scolefin[®] 24 T 20-0

Polypropylene
Prime Compound

Description:

PP Copolymer, 40% talcum filled, natural

General

MFI (230°/2,16kg)	ISO 1133	1.5	g/10min
Density	ISO 1183	1.24	g/cm ³

Thermal

HDT/A (1,82MPa)	ISO 75A	65	°C
-----------------	---------	----	----

Mechanical

Charpy notched impact strength (23 °C)	ISO 179	5	kJ/m ²
Charpy unnotched impact strength (23 °C)	ISO 179	40	kJ/m ²
Tensile stress at yield	ISO 527	27	MPa
Tensile modulus	ISO 527	3200	MPa
Flex modulus	ISO 178	2900	MPa

Various

Ash content (625°C)	DIN EN 60	40	%
---------------------	-----------	----	---

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters

Moerenstraat 85A
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11
Fax: +32 (0)14 67 20 12

www.ravago.com
manufacturing@ravago.com

Issue Date:
Nov 2018