

# Scolefin<sup>®</sup> 33 T 10-1

Polypropylene  
Prime Compound

## Description:

PP homopolymer, 30 % talcum filled, heat-stabilized, white compound

## General

MFI (230°/2,16kg)	ISO 1133	6	g/10min
Density	ISO 1183	1.15	g/cm <sup>3</sup>

## Thermal

HDT/A (1,82MPa)	ISO 75A	70	°C
-----------------	---------	----	----

## Mechanical

Charpy notched impact strength (23 °C)	ISO 179	3	kJ/m <sup>2</sup>
Charpy unnotched impact strength (23 °C)	ISO 179	30	kJ/m <sup>2</sup>
Tensile modulus	ISO 527	3600	MPa
Flex modulus	ISO 178	3200	MPa

## Various

Ash content (700 °C)	ISO 3451	30	%
----------------------	----------	----	---

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## Ravago Group Headquarters

Moerenstraat 85A  
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11  
Fax: +32 (0)14 67 20 12

www.ravago.com  
manufacturing@ravago.com

Issue Date:  
Nov 2018