

Scolefin[®] 36 G 10-0

Polypropylene
Prime Compound

Description:

PPH Compound, 60% glass filled, natural

General

MFI (230°/2,16kg)	ISO 1133	4	g/10min
-------------------	----------	---	---------

Thermal

HDT/A (1,82MPa)	ISO 75A	150	°C
-----------------	---------	-----	----

Mechanical

Charpy notched impact strength (23 °C)	ISO 179	11	kJ/m ²
Charpy unnotched impact strength (23 °C)	ISO 179	47	kJ/m ²
Tensile stress at yield	ISO 527	110	MPa
Tensile modulus	ISO 527	15000	MPa
Flex modulus	ISO 178	13000	MPa

Various

Ash content (600 °C)	ISO 3451	60	%
----------------------	----------	----	---

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters

Moerenstraat 85A
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11
Fax: +32 (0)14 67 20 12

www.ravago.com
manufacturing@ravago.com

Issue Date:
Apr 2018