

# ■ Scolefin<sup>®</sup> 43 H 10-9

Polypropylene  
Prime Compound

## Description:

Polypropylene homopolymer, 20% talc, 10% glass fiber filled

## General

MFI (230°/2,16kg)	ISO 1133	10	g/10min
Density	ISO 1183	1.15	g/cm <sup>3</sup>

## Thermal

Vicat softening point (B50 (50N))	ISO 306	114	°C
-----------------------------------	---------	-----	----

## Mechanical

Izod notched impact strength (23°C)	ISO 180/A	4.5	kJ/m <sup>2</sup>
Flex modulus	ISO 178	4000	MPa

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## Ravago Group Headquarters

Moerenstraat 85A  
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11  
Fax: +32 (0)14 67 20 12

www.ravago.com  
manufacturing@ravago.com

Issue Date:  
Jun 2015