

■ Scolefin[®] 46 B 20-9

Polypropylene
Prime

Description:

PP copolymer, 60% barium sulphate filled, black colour, for injection moulding applications

General

MFI (230°/2,16kg)	ISO 1133	10	g/10min
Density	ISO 1183	1,69	g/cm ³

Thermal

Vicat softening point (B50 (50N))	ISO 306	57	°C
-----------------------------------	---------	----	----

Mechanical

Izod notched impact strength (23 °C)	ISO 180	11,4	kJ/m ²
Tensile strength at yield (23 °C)	ISO 527	11	MPa
Flexural modulus (23 °C)	ISO 178	1650	MPa

Remark:

Provisional Datasheet

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters

Moerenstraat 85A
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11
Fax: +32 (0)14 67 20 12

www.ravago.com
manufacturing@ravago.com

Issue Date:
Oct 2021