

Scolefin[®] 61 M 23

Polypropylene
Prime Compound

Description:

PP Prime compound, light weight, aesthetical surface, excellent balance impact-stiffness, scratch resistant, for interior automotive trims, coloured on request

General

MFI (230°/2,16kg)	ISO 1133	15	g/10min
Density	ISO 1183	0,98	g/cm ³

Mechanical

Izod notched impact strength (23 °C)	ISO 180	25	kJ/m ²
Tensile strength at yield (23 °C)	ISO 527	17	MPa
Tensile strength at break (23 °C)	ISO 527	12	MPa
Elongation at break (23 °C)	ISO 527	48	%
Tensile modulus (23 °C)	ISO 527	1450	MPa
Flexural modulus (23 °C)	ISO 178	1600	MPa

Various

Ash content (600 °C)	ISO 3451	10	%
----------------------	----------	----	---

Remark:

Provisional datasheet

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters

Moerenstraat 85A
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11
Fax: +32 (0)14 67 20 12

www.ravago.com
manufacturing@ravago.com

Issue Date:
May 2019