

# Scolefin<sup>®</sup> 61 M 24

Polypropylene  
Prime Compound

## Description:

PP/EPR blend, 10% mineral filled, impact modified, scratch resistance

## General

MFI (230°/2,16kg)	ISO 1133	13	g/10min
Density	ISO 1183	0,98	g/cm <sup>3</sup>

## Mechanical

Izod notched impact strength (23°C)	ISO 180	24	kJ/m <sup>2</sup>
Tensile stress at yield	ISO 527	24	MPa
Elongation at yield	ISO 527	4	%
Elongation at break	ISO 527	10	%
Tensile modulus	ISO 527	2300	MPa
Flex modulus	ISO 178	2500	MPa

## Various

Ash content (600 °C)	ISO 3451	10	%
----------------------	----------	----	---

## Remark:

PROVISIONAL DATASHEET

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## Ravago Group Headquarters

Moerenstraat 85A  
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11  
Fax: +32 (0)14 67 20 12

www.ravago.com  
manufacturing@ravago.com

Issue Date:  
Feb 2019