

# Scolefin<sup>®</sup> 62 T 20-0

Polypropylene  
Prime Compound

## Description:

PP Copolymer, 20% talc filled improved flowability

## General

MFI (230°/2,16kg)	ISO 1133	20	g/10min
Density	ISO 1183	1.04	g/cm <sup>3</sup>

## Thermal

HDT/B (0,46MPa)	ISO 75B	115	°C
-----------------	---------	-----	----

## Mechanical

Izod notched impact strength (23°C)	ISO 180	5	kJ/m <sup>2</sup>
Elongation at break	ISO 527	24	%
Tensile modulus	ISO 527	2000	MPa
Flex modulus	ISO 178	2100	MPa
Tensile strength	ISO 527	25	MPa

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## Ravago Group Headquarters

Moerenstraat 85A  
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11  
Fax: +32 (0)14 67 20 12

www.ravago.com  
manufacturing@ravago.com

Issue Date:  
Jan 2018