

# Scolefin<sup>®</sup> 62 T 26

Polypropylene  
Prime Compound

## Description:

PP prime compound, 20% talcum filled, high scratch resistant, for interior automotive trims, coloured on request

## General

MFI (230°/2,16kg)	ISO 1133	16	g/10min
Density	ISO 1183	1,05	g/cm <sup>3</sup>

## Thermal

Vicat softening point (B50 (50N))	ISO 306	50	°C
-----------------------------------	---------	----	----

## Mechanical

Izod notched impact strength (23°C)	ISO 180	18	kJ/m <sup>2</sup>
Tensile stress at yield	ISO 527	20	MPa
Elongation at yield	ISO 527	4	%
Tensile modulus	ISO 527	1900	MPa
Flex modulus	ISO 178	2000	MPa

## Various

Ash content (700 °C)	ISO 3451	20	%
----------------------	----------	----	---

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## Ravago Group Headquarters

Moerenstraat 85A  
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11  
Fax: +32 (0)14 67 20 12

www.ravago.com  
manufacturing@ravago.com

Issue Date:  
Sep 2019