

RavaSafe® ZH-LSF 1 is a thermoplastic zero halogen, low smoke flame retardant compound designed for general purpose sheathing application.

This compound combines excellent processing and good mechanical properties.

Typical Application: OFC/DATA/LAN/telecom/HM4/IEC 60332-1, single flame test, general purpose sheathing with great line speed.

Standard norms (type of material) : EN 50363 (TI7, TM7), VDE 0207 / 0250 (HM2, HM4, HI2), BS 7655 (LTS 2), IEC 60502 (ST8) and IEC 60092-360 (SHF1)

Technical properties:

Physical and Mechanical Properties	Typical Value	Units (SI)	Test Method
Density, 23°C	1,51	g/cm³	ISO 1183-1 (ASTM D792)
Melt flow index (150°C /21,6kg)	4	g/10 min	ISO 1133 (b)
Hardness (15 seconds)	41	Shore D	ISO R 868 (ASTM D2240)
Water immersion test (7d @ 70°C)	1,3	mg/cm²	IEC 60811-402
Tear strength 23°C	8,5	N/mm	BS 6469-99.1
Unaged mechanical properties (200 mm/min)			
Tensile strength	11,4	MPa	IEC 60811-501
Elongation at break	184	%	
Thermal ageing 7 days at 120°C			
Tensile strength variation (Δ)	17	%	IEC 60811-501
Elongation at break variation (Δ)	-9	%	
Thermal Mechanical Properties			
Hot Pressure Deformation (6h @ 90°C)	< 50	%	IEC 60811-508
Oil resistance test 4h at 70°C (IRM 902 – immersion)			
Tensile strength variation (Δ)	-13	%	IEC 60811-404
Elongation at break variation (Δ)	17	%	

Flammability	Typical Value	Units (SI)	Test Method
Oxygen Index	37	%	ISO 4589-2 (ASTM D2863)
Temperature Index	> 310	°C	ISO 4589-3
Halogen content	< 0,5	%	IEC 60754-1
<i>Acid gas emission</i>			
pH	> 4,3	/	IEC 60754-2
Conductivity	< 2,5	μS/mm	IEC 60754-1

Recommended extrusion profile:

Extrusion Temperatures	Zones							
	Z1	Z2	Z3	Z4	Z5	Collar	Head	Die
Temperature (Imperial)	266°F	284°F	302°F	320°F	320°F	329°F	338°F	338°F
Temperature (SI)	130°C	140°C	150°C	160°C	160°C	165°C	170°C	170°C

RavaSafe® ZH-LSF 1 is a product able to run on standard extruders, based on low compression screw and head. This compound is supplied in aluminium foil bags. Pre-drying is not required before extrusion process.

RavaSafe® ZH-LSF 1 is colorable. A full range of specific color masterbatches (RAVACOLOR™) and additive masterbatches (RAVABOOST™) are available.

For any further information, please contact Ravago W&C.

The material description is subject to changes during the validation period of the product.

This product information is based on our general experience and does not constitute a specification. Since many factors affect the use of our products, no warranty is given or implied with respect to this information or patent infringement. We do not accept liability for any loss or damage arising from the use of this information. All sales are subject to our Standard Terms and Conditions of Sale.