

RavaSafe® ZH-LSF 4Z2 is a thermoplastic zero halogen, low smoke flame retardant compound designed for high mechanical properties sheathing.

This solution is UV stabilized and has a good low and high temperature behavior.

Technical features: DMZ-2, DMO-2 and ST12

Technical properties:

Physical and Mechanical Properties	Typical Value	Units (SI)	Test Method		
Density, 23°C	1,51	g/cm³	ISO 1183-1 (ASTM D792)		
Melt flow index (150°C /21,6kg)	3	g/10 min	ISO 1133 (b)		
Hardness (15 seconds)	45	Shore D	ISO R 868 (ASTM D2240)		
Water immersion test (7d @ 70°C)	0,1	mg/cm²	IEC 60811-402		
Water immersion test (14d @ 85°C)	1,06	mg/cm²	IEC 60811-402		
Tear strength 23ºC	19,4	N/mm	BS 6469-99.1		
Unaged mechanical properties (200 mm/min)					
Tensile strength	> 13	MPa	IEC 60811-501		
Elongation at break	> 400	%	IEC 00811-501		
Thermal ageing 7 days at 120°C					
Tensile strength variation (Δ)	16	%	IEC 60811-501		
Elongation at break variation (Δ)	-15	%	IEC 00011-501		
Thermal ageing 10 days at 110°C					
Tensile strength variation (Δ)	> 15	%	IEC 60811-501		
Elongation at break variation (Δ)	> 300	%	IEC 00011-501		
Thermal Mechanical Properties					
Hot Pressure Deformation (6h @ 90°C)	< 50	%	IEC 60811-508		
Hot Pressure Deformation (6h @ 110°C)	< 50	%	IEC 60811-508		
Loss of mass (7d @ 100°C)	0,01	mg/cm ²	IEC 60811-409		
Shrinkage (5h @ 80°C)	0,2	%	IEC 60811-502 & 503		
Elongation at break (-40°C)	> 60	%	IEC60811-505		

Flammability	Typical Value	Units (SI)	Test Method				
Oxygen Index	30	%	ISO 4589-2 (ASTM D2863)				
Halogen content	< 0,5	%	IEC 60754-1				
Acid gas emission							
рН	> 4,3	/	IEC 60754-2				
Conductivity	< 2,5	μS/mm	IEC 60754-1				

Recommended extrusion profile:

Extrusion Temperatures	Zones							
	Z1	Z2	Z3	Z4	Z5	Collar	Head	Die
Temperature (Imperial)	266°F	284°F	302°F	320°F	320°F	329°F	338°F	338°F
Temperature (SI)	140°C	150°C	160°C	170°C	170°C	175°C	180°C	180°C

RavaSafe® ZH-LSF 4Z2 is a product able to run on standard extruders, based on low compression screw and head. This compound is supplied in aluminium foil bags. Pre-drying is not required before extrusion process.

RavaSafe® ZH-LSF 4Z2 is colorable. A full range of specific color masterbatches (RAVACOLOR^M) and additive masterbatches (RAVABOOST^M) are available.

For any further information, please contact Ravago W&C.

The material description is subject to changes during the validation period of the product.

This product information is based on our general experience and does not constitute a specification. Since many factors affect the use of our products, no warranty is given or implied with respect to this information or patent infringement. We do not accept liability for any loss or damage arising from the use of this information. All sales are subject to our Standard Terms and Conditions of Sale.