

Mafill® CR E 3144

Polypropylene
Industrial Quality Compound

Description:

PP/PE compound talcum filled

General

MFI (230°/2,16kg)	ISO 1133	5	g/10min
Density	ISO 1183	0.97	g/cm ³
Linear mould shrinkage	ASTM D955	1.0-1.5	%

Thermal

Vicat softening point (B50 (50N))	ISO 306	50	°C
-----------------------------------	---------	----	----

Mechanical

Izod notched impact strength (23 °C)	ISO 180	15	kJ/m ²
Tensile strength at yield (23 °C)	ISO 527	18	MPa
Tensile strength at break (23 °C)	ISO 527	14	MPa
Elongation at break (23 °C)	ISO 527	30	%
Flexural modulus (23 °C)	ISO 178	800	MPa

Flammability

Flammability (1,6mm)	UL94 (tested internally)	HB
Flammability (3,2mm)	UL94 (tested internally)	HB

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters

Moerenstraat 85A
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11
Fax: +32 (0)14 67 20 12

www.ravago.com
manufacturing@ravago.com

Issue Date:
Jun 2023