

# Mafill® CR XC 3549 B Grey

Polypropylene  
Industrial Quality Compound

## Description:

Polypropylene, 30% finest calcium carbonate filled, designed for extrusion applications, carbon black free.

## General

MFI (230°/2,16kg)	ISO 1133	5	g/10min
Density	ISO 1183	1.14	g/cm <sup>3</sup>
Linear mould shrinkage	ASTM D955	0,8-1,3	%

## Thermal

Vicat softening point (B50 (50N))	ISO 306	80	°C
-----------------------------------	---------	----	----

## Mechanical

Izod notched impact strength (23 °C)	ISO 180	3.5	kJ/m <sup>2</sup>
Flexural modulus (23 °C)	ISO 178	1600	MPa

## Flammability

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## Ravago Group Headquarters

Moerenstraat 85A  
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11  
Fax: +32 (0)14 67 20 12

www.ravago.com  
manufacturing@ravago.com

Issue Date:  
Apr 2023