

Ravapura® ABS 7022

ABS

Recycled Quality Compound



Description:

ABS compound based on Post Consumer Recycled material, standard injection molding grade general purpose, good aesthetical properties, containing minimum 70% PCR.
Available only in selected colors

General

MFI (220°C/10kg)	ISO 1133	22	g/10min
------------------	----------	----	---------

Thermal

HDT/A (1,82MPa)	ISO 75A	91	°C
Vicat softening point (B50 (50N))	ISO 306	97	°C
Ball pressure test (75°C)	IEC 60695-10-2	pass	°C

Mechanical

Izod notched impact strength (23 °C)	ISO 180	14	kJ/m ²
Tensile strength at yield (23 °C)	ISO 527	35	MPa
Elongation at break (23 °C)	ISO 527	15	%
Flexural modulus (23 °C)	ISO 178	2200	MPa

Flammability

Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C
---------------------------------------	----------------	-----	----

Various

Surface resistivity	IEC 60093	1E15	Ohm
Volume resistivity	IEC 60093	1E14	Ohm.cm
Linear Mould Shrinkage	internal method	0,4-0,7	%

Remark:

Preliminary Data Sheet

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago Recycled Quality are ISO 14021:2016 compliant. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application

Ravago Group Headquarters

Moerenstraat 85A
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11
Fax: +32 (0)14 67 20 12

www.ravago.com
manufacturing@ravago.com

Issue Date:
May 2022

Page 1 of 1