

Scolefin[®] 53 T 10

Polypropylene Prime Compound

Description:

PPH, 30% talc filled, natural

General			
MFI (230°/2,16kg) Density	ISO 1133 ISO 1183	12 1.135	g/10min g/cm³
Thermal			
Vicat softening point (B50 (50N))	ISO 306	100	°C
Mechanical			
Izod notched impact strength (23 °C)	ISO 180	3	kJ/m²
Flexural modulus (23 °C)	ISO 178	3000	MPa
Flammability			
Glow wire flammability index (3mm)	IEC 60695-2-12	650	°C

Remark:

Different colors available:

- Scolefin 53 T 10-9: black version
- Scolefin 53 T 10-0: natural version

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters

Tel: +32 (0)14 67 25 11 Fax: +32 (0)14 67 20 12 www.ravago.com Issue Date: manufacturing@ravago.com Feb 2024

Page 1 of 1