

RavaCabl® PPc S-4 is a polypropylene thermoplastic compound designed for a telecom insulation application.

It presents excellent extrudability under thin wall thickness with good mechanical and thermal properties.

Technical properties:

Physical and Mechanical Properties	Typical Value	Units (SI)	Test Method
Density, 23°C	0,9	g/cm³	ISO 1183-1 (ASTM D792)
Bulk Density	0,48	g/cm³	ISO 60
Melt flow index (230°C / 2,16kg)	1,5	g/10 min	ISO 1133 (b)
Hardness (15 seconds)	40	Shore D	ISO R 868 (ASTM D2240)
Unaged mechanical properties (50 mm/min)			
Tensile strength	>25	MPa	IEC 60811
Elongation at break	>450	%	
Thermal ageing 7 days at 100°C			
Tensile strength variation (Δ)	<30	%	IEC 60811
Elongation at break variation (Δ)	<30	%	
Thermal ageing 7 days at 121°C			
Tensile strength variation (Δ)	<30	%	UL 1581
Elongation at break variation (Δ)	<30	%	

Recommended extrusion profile:

Extrusion Temperatures	Zones							
	Z1	Z2	Z3	Z4	Z5	Collar	Head	Die
Temperature (Imperial)	356°F	374°F	392°F	410°F	428°F	428°F	428°F	428°F
Temperature (SI)	180°C	190°C	200°C	210°C	220°C	220°C	220°C	220°C

RavaCabl® PPc S-4 is a product able to run on standard extruders, based on low compression screw and head. This compound is supplied in bags.. Pre-drying is not required before extrusion process.

RavaCabl® PPc S-4 is colorable. A full range of specific color masterbatches (RAVACOLOR™) and additive masterbatches (RAVABOOST™) are available.

For any further information, please contact Ravago W&C.

The material description is subject to changes during the validation period of the product.

This product information is based on our general experience and does not constitute a specification. Since many factors affect the use of our products, no warranty is given or implied with respect to this information or patent infringement. We do not accept liability for any loss or damage arising from the use of this information. All sales are subject to our Standard Terms and Conditions of Sale.